



UNITED STATES PATENT AND TRADEMARK OFFICE

UNITED STATES DEPARTMENT OF COMMERCE
United States Patent and Trademark Office
Address: COMMISSIONER FOR PATENTS
P.O. Box 1450
Alexandria, Virginia 22313-1450
www.uspto.gov

APPLICATION NO.	FILING DATE	FIRST NAMED INVENTOR	ATTORNEY DOCKET NO.	CONFIRMATION NO.
10/645,836	08/22/2003	Philip J. Lingle	3691-583	8131

23117 7590 06/17/2005

NIXON & VANDERHYE, PC
901 NORTH GLEBE ROAD, 11TH FLOOR
ARLINGTON, VA 22203

EXAMINER

BLACKWELL RUDASIL, GWENDOLYN A

ART UNIT	PAPER NUMBER
----------	--------------

1775

DATE MAILED: 06/17/2005

Please find below and/or attached an Office communication concerning this application or proceeding.

Office Action Summary

Application No.

10/645,836

Applicant(s)

LINGLE ET AL.

Examiner

Gwendolyn Blackwell

Art Unit

1775

-- The MAILING DATE of this communication appears on the cover sheet with the correspondence address --

Period for Reply

A SHORTENED STATUTORY PERIOD FOR REPLY IS SET TO EXPIRE 3 MONTH(S) FROM THE MAILING DATE OF THIS COMMUNICATION.

- Extensions of time may be available under the provisions of 37 CFR 1.136(a). In no event, however, may a reply be timely filed after SIX (6) MONTHS from the mailing date of this communication.
- If the period for reply specified above is less than thirty (30) days, a reply within the statutory minimum of thirty (30) days will be considered timely.
- If NO period for reply is specified above, the maximum statutory period will apply and will expire SIX (6) MONTHS from the mailing date of this communication.
- Failure to reply within the set or extended period for reply will, by statute, cause the application to become ABANDONED (35 U.S.C. § 133). Any reply received by the Office later than three months after the mailing date of this communication, even if timely filed, may reduce any earned patent term adjustment. See 37 CFR 1.704(b).

Status

- 1) ☐ Responsive to communication(s) filed on ____.
- 2a) ☐ This action is **FINAL**. 2b) ☒ This action is non-final.
- 3) ☐ Since this application is in condition for allowance except for formal matters, prosecution as to the merits is closed in accordance with the practice under *Ex parte Quayle*, 1935 C.D. 11, 453 O.G. 213.

Disposition of Claims

- 4) ☒ Claim(s) 1-44 is/are pending in the application.
- 4a) Of the above claim(s) ____ is/are withdrawn from consideration.
- 5) ☐ Claim(s) ____ is/are allowed.
- 6) ☒ Claim(s) 1-44 is/are rejected.
- 7) ☐ Claim(s) ____ is/are objected to.
- 8) ☐ Claim(s) ____ are subject to restriction and/or election requirement.

Application Papers

- 9) ☐ The specification is objected to by the Examiner.
- 10) ☒ The drawing(s) filed on 22 August 2003 is/are: a) ☒ accepted or b) ☐ objected to by the Examiner.
Applicant may not request that any objection to the drawing(s) be held in abeyance. See 37 CFR 1.85(a).
Replacement drawing sheet(s) including the correction is required if the drawing(s) is objected to. See 37 CFR 1.121(d).
- 11) ☐ The oath or declaration is objected to by the Examiner. Note the attached Office Action or form PTO-152.

Priority under 35 U.S.C. § 119

- 12) ☐ Acknowledgment is made of a claim for foreign priority under 35 U.S.C. § 119(a)-(d) or (f).
- a) ☐ All b) ☐ Some * c) ☐ None of:
- ☐ Certified copies of the priority documents have been received.
 - ☐ Certified copies of the priority documents have been received in Application No. ____.
 - ☐ Copies of the certified copies of the priority documents have been received in this National Stage application from the International Bureau (PCT Rule 17.2(a)).

* See the attached detailed Office action for a list of the certified copies not received.

Attachment(s)

- | | |
|---|---|
| 1) <input checked="" type="checkbox"/> Notice of References Cited (PTO-892) | 4) <input type="checkbox"/> Interview Summary (PTO-413)
Paper No(s)/Mail Date. ____. |
| 2) <input type="checkbox"/> Notice of Draftsperson's Patent Drawing Review (PTO-948) | 5) <input type="checkbox"/> Notice of Informal Patent Application (PTO-152) |
| 3) <input checked="" type="checkbox"/> Information Disclosure Statement(s) (PTO-1449 or PTO/SB/08)
Paper No(s)/Mail Date <u>9/03</u> . | 6) <input type="checkbox"/> Other: ____. |

DETAILED ACTION

Information Disclosure Statement

1. US Patent Application no. 60/217,101 listed on the Information Disclosure Statement labeled August 22, 2003 has been noted and considered. However, because the document is not published, it will not be listed on the front of any patent granted in this presently pending application.

Claim Rejections - 35 USC § 102

2. The following is a quotation of the appropriate paragraphs of 35 U.S.C. 102 that form the basis for the rejections under this section made in this Office action:

A person shall be entitled to a patent unless –

(b) the invention was patented or described in a printed publication in this or a foreign country or in public use or on sale in this country, more than one year prior to the date of application for patent in the United States.

(e) the invention was described in (1) an application for patent, published under section 122(b), by another filed in the United States before the invention by the applicant for patent or (2) a patent granted on an application for patent by another filed in the United States before the invention by the applicant for patent, except that an international application filed under the treaty defined in section 351(a) shall have the effects for purposes of this subsection of an application filed in the United States only if the international application designated the United States and was published under Article 21(2) of such treaty in the English language.

3. Claims 1-5, 9-14, 22-27, 31-33, 38-42, and 44 are rejected under 35 U.S.C. 102(b) as being anticipated by United States Patent no. 6,060,178, Krisko.

Regarding claim 1

Applicant claims the following layer structure, (claim 1):

glass/silicon nitride/zinc oxide/Ag/dielectric (metal oxide)/Ag/dielectric

wherein the glass, silicon nitride, zinc oxide and first Ag layers are all located on and contacting each other without any other layers located between the aforementioned layers.

Krisko disclose a coated article comprised of a glass substrate with a multilayer coating formed thereon which is able to withstand the high temperatures associated with heat

Art Unit: 1775

treatment, (column 1, lines 10-15). Example 2 demonstrates the following layer structure, (column 8, lines 35-59), meeting the requirements of claim 1:

Glass	
Si ₃ N ₄	86 Å
ZnO	50 Å
Ag	77 Å
Nb	15 Å
ZnO	90 Å
Si ₃ N ₄	470 Å
ZnO	50 Å
Ag	145 Å
Nb	15 Å
ZnO	90 Å
Si ₃ N ₄	245 Å

Regarding claims 2-5, 10-14 and 22

When the structure recited in the reference is substantially identical to that of the claims, the claimed properties or function are presumed inherent. *MPEP 2112.01*. Because Example 2 of Krisko (see above) exemplifies Applicant's claimed multilayer coating structure, the claimed physical properties relating to the visible light transmission, sheet resistance, and ΔE^* are inherently present in the prior art. Absent an objective showing to the contrary, the addition of the claimed physical properties to the claim language fails to provide patentable distinction over the prior art of record, meeting the requirements of claims 2-5 and 10-14.

Because the layer structure of Example 2 exemplifies the layer structure of presently pending claim 1 as demonstrated above, it would be expected that when the layer structure of Example 2 when heated according to the specifications of claim 22 that it would exhibit the same properties. Absent an objective showing to the contrary, the addition of the claimed physical properties to claim 22 fails to provide a patentable distinction over the prior art of record, meeting the limitations of claim 22.

Regarding claim 9 and 31

The silicon nitride layer formed next to the glass substrate can have a thickness ranging from 50-300 Å, (column 7, lines 26-29), meeting the requirements of claims 9 and 31.

Regarding claim 23

Applicant claims the following layer structure, (claim 23):

glass/silicon nitride/zinc oxide/Ag/dielectric

wherein the silicon nitride is located directly on and contacting the glass substrate and the Ag layer is located directly on and contacting the zinc oxide layer. Krisko disclose a coated article comprised of a glass substrate with a multilayer coating formed thereon which is able to withstand the high temperatures associated with heat treatment, (column 1, lines 10-15). Example 2 of Krisko demonstrates the following layer structure, (column 8, lines 35-59), meeting the requirements of claim 23:

Glass	
Si ₃ N ₄	86 Å
ZnO	50 Å
Ag	77 Å
Nb	15 Å
ZnO	90 Å
Si ₃ N ₄	470 Å
ZnO	50 Å
Ag	145 Å
Nb	15 Å
ZnO	90 Å
Si ₃ N ₄	245 Å

Regarding claims 24-27, 32-33, and 38

When the structure recited in the reference is substantially identical to that of the claims, the claimed properties or function are presumed inherent. *MPEP 2112.01*. Because Example 2 of Krisko (see above) exemplifies Applicant's claimed multilayer coating structure, the claimed physical properties relating to the visible light transmission, sheet resistance, and ΔE^* are inherently present in the prior art. Absent an objective showing to the contrary, the addition of the claimed physical properties to the claim language fails to provide patentable distinction over the prior art of record, meeting the requirements of claims 24-27 and 32-33.

Because the layer structure of Example 2 exemplifies the layer structure of presently pending claim 23 as demonstrated above, it would be expected that when the layer structure of Example 2 when heated according to the specifications of claim 22 that it would exhibit the same properties. Absent an objective showing to the contrary, the addition of the claimed physical properties to claim 38 fails to provide a patentable distinction over the prior art of record, meeting the limitations of claim 38.

Regarding claims 39-42

Applicant claims the following layer structure, (claim 39):

glass/silicon nitride/metal oxide/Ag/dielectric

wherein the silicon nitride is located directly on and contacting the glass substrate and the Ag layer is located directly on and contacting the metal oxide layer. Krisko disclose a coated article comprised of a glass substrate with a multilayer coating formed thereon which is able to withstand the high temperatures associated with heat treatment, (column 1, lines 10-15). Example 2 demonstrates the following layer, (column 8, lines 35-59):

Art Unit: 1775

Glass	
Si ₃ N ₄	86 Å
ZnO	50 Å
Ag	77 Å
Nb	15 Å
ZnO	90 Å
Si ₃ N ₄	470 Å
ZnO	50 Å
Ag	145 Å
Nb	15 Å
ZnO	90 Å
Si ₃ N ₄	245 Å

When the structure recited in the reference is substantially identical to that of the claims, the claimed properties or function are presumed inherent. *MPEP 2112.01*. Because the layer structure of Example 2 exemplifies the layer structure of presently pending claim 39 as demonstrated above, it would be expected that when the layer structure of Example 2 when heated according to the specifications of claim 39 that it would exhibit the same physical properties. Absent an objective showing to the contrary, the addition of the claimed physical properties to claim 39 fails to provide a patentable distinction over the prior art of record, meeting the limitations of claims 39-42.

Regarding claim 44

The coated substrate, which is be held synonymous with a monolithic glass substrate, can be formed of a glass substrate with a multilayer coating formed thereon that is used as a window of a self-cleaning oven, (column 3, lines 39-44), meeting the requirements of claim 44.

4. Claims 1-5, 8, 10-14, 16-17, 19-27, 30, 32-33, 35-37, 39-42, and 44 are rejected under 35 U.S.C. 102(e) as being anticipated by United States Patent no. 6,472,072, Ebisawa et al.

Regarding claims 1

Applicant claims the following layer structure, (claim 1):

glass/silicon nitride/zinc oxide/Ag/dielectric (metal oxide)/Ag/dielectric

Art Unit: 1775

wherein the glass, silicon nitride, zinc oxide and first Ag layers are all located on and contacting each other without any other layers located between the aforementioned layers.

Ebisawa et al disclose a glazing panel having the following structure, (Example 1, column 6, lines 45-64), meeting the requirements of claim 1:

	Reference number	Geometrical thickness	Atomic ratios
Glass substrate	10	2 mm	
Base dielectric comprising:	11		
AlSiN _y	12	40 Å	Si/Al = 0.5
ZnAlO _x	13	260 Å	Al/Zn = 0.1
ZnAlO _y underlying barrier	14	10 Å	Al/Zn = 0.1
Ag	15	100 Å	
ZnAlO _y overlying barrier	16	12 Å	Al/Zn = 0.1
Central dielectric comprising:			
ZnAlO _x	17	770 Å	Al/Zn = 0.1
ZnAlO _y underlying barrier	18	7 Å	Al/Zn = 0.1
Ag	19	100 Å	
ZnAlO _y overlying barrier	20	17 Å	Al/Zn = 0.1
Top dielectric comprising:			
ZnAlO _x	21	185 Å	Al/Zn = 0.1
AlSiN _y	22	75 Å	Si/Al = 0.3

Regarding claims 2-5, 10-14 and 22

When the structure recited in the reference is substantially identical to that of the claims, the claimed properties or function are presumed inherent. *MPEP 2112.01*. Because Example 1 of Ebisawa et al (see above) exemplifies Applicant's claimed multilayer coating structure, the claimed physical properties relating to the visible light transmission, sheet resistance, and ΔE^* are inherently present in the prior art. Absent an objective showing to the contrary, the addition of the claimed physical properties to the claim language fails to provide patentable distinction over the prior art of record, meeting the requirements of claims 2-5 and 10-14.

Because the layer structure of Example 1 exemplifies the layer structure of presently pending claim 1 as demonstrated above, it would be expected that when the layer structure of Example 1 when heated according to the specifications of claim 22 that it would exhibit the

Art Unit: 1775

same properties. Absent an objective showing to the contrary, the addition of the claimed physical properties to claim 22 fails to provide a patentable distinction over the prior art of record, meeting the limitations of claim 22.

Regarding claims 8, 16, 30, and 44

The glazing panel can be used in a laminated vehicle windscreen wherein after heat treatment the first layer comprised of silicon nitride which is next to the glass substrate is partially oxidized resulting in some silicon oxynitride being present in the layer, meeting the requirements of claim 44.

Because Example 1 after heat treatment, (columns 7-8, lines 58-20), of Ebisawa et al exemplifies Applicant's claimed multilayer coating structure, the claimed physical property relating to the index of refraction is inherently present in the prior art. Absent an objective showing to the contrary, the addition of the claimed physical property to the claim language fails to provide patentable distinction over the prior art of record, meeting the requirements of claims 8, 16, and 30.

Regarding claims 17 and 35

According to Example 1 set forth above the zinc oxide and silicon nitride layer further includes aluminum, meeting the requirements of claims 17 and 35.

Regarding claims 19-21 and 36-37

According to Example 1 the laminated vehicle windscreen has the following properties:

Property	Prior to heat treatment ^{Note 1} below	Following heat treatment ^{Note 2} below
TL (Illuminant A)	65%	76%
TE (System Moon 2)	40%	43%
haze	0.1	0.2
a*	-15 (coated side)	-2 (external)
b*	+1 (coated side)	-10 (external)
RE (System Moon 2)	29% (coated side)	31% (external)

Note 1: Measure for monolithic glazing panel with coating prior to heat treatment.
Note 2: Measured following heat treatment at 650° C. for 10 minutes with bending and tempering, and lamination with clear 2 mm glass sheet and 0.76 mm clear pvb.

Art Unit: 1775

wherein the total solar value as exemplified by Applicant is being held synonymous with Ebisawa et al's TE value, meeting the requirements of claims 19-21 and 36-37.

Regarding claim 23

Applicant claims the following layer structure, (claim 23):

glass/silicon nitride/zinc oxide/Ag/dielectric

wherein the silicon nitride is located directly on and contacting the glass substrate and the Ag layer is located directly on and contacting the zinc oxide layer. Ebisawa et al disclose a glazing panel having the following structure, (Example 1, column 6, lines 45-64), meeting the requirements of claim 23:

	Reference number	Geometrical thickness	Atomic ratios
Glass substrate	10	2 mm	
Base dielectric comprising:	11		
AlSiN _x	12	40 Å	Si/Al = 0.5
ZnAlO _x	13	250 Å	Al/Zn = 0.1
ZnAlO _y underlying barrier	14	10 Å	Al/Zn = 0.1
Ag	15	100 Å	
ZnAlO _y overlying barrier	16	12 Å	Al/Zn = 0.1
Central dielectric comprising:			
ZnAlO _x	17	770 Å	Al/Zn = 0.1
ZnAlO _y underlying barrier	18	7 Å	Al/Zn = 0.1
Ag	19	100 Å	
ZnAlO _y overlying barrier	20	17 Å	Al/Zn = 0.1
Top dielectric comprising:			
ZnAlO _x	22	185 Å	Al/Zn = 0.1
AlSiN _x	23	75 Å	Si/Al = 0.3

Regarding claims 24-27, 32-33, and 38

When the structure recited in the reference is substantially identical to that of the claims, the claimed properties or function are presumed inherent. *MPEP 2112.01*. Because Example 1 of Ebisawa et al (see above) exemplifies Applicant's claimed multilayer coating structure, the claimed physical properties relating to the visible light transmission, sheet resistance, and ΔE^* are inherently present in the prior art. Absent an objective showing to the contrary, the addition of the claimed physical properties to the claim language fails to

Art Unit: 1775

provide patentable distinction over the prior art of record, meeting the requirements of claims 24-27 and 32-33.

Because the layer structure of Example 1 exemplifies the layer structure of presently pending claim 23 as demonstrated above, it would be expected that when the layer structure of Example 1 when heated according to the specifications of claim 22 that it would exhibit the same properties. Absent an objective showing to the contrary, the addition of the claimed physical properties to claim 38 fails to provide a patentable distinction over the prior art of record, meeting the limitations of claim 38.

Regarding claims 39-42

Applicant claims the following layer structure, (claim 39):

glass/silicon nitride/metal oxide/Ag/dielectric

wherein the silicon nitride is located directly on and contacting the glass substrate and the Ag layer is located directly on and contacting the metal oxide layer. Ebisawa et al disclose a glazing panel having the following structure, (Example 1, column 6, lines 45-64), meeting the requirements of claim 39:

	Reference number	Geometrical thickness	Atomic ratios
Glass substrate	10	2 mm	
Base dielectric comprising:	11		
AlSi _x N _y	12	40 Å	Si/Al = 0.5
ZnAlO _x	13	250 Å	Al/Zn = 0.1
ZnAlO _y underlying barrier	14	10 Å	Al/Zn = 0.1
Ag	15	100 Å	
ZnAlO _y overlying barrier	16	12 Å	Al/Zn = 0.1
Central dielectric comprising			
ZnAlO _x	17	770 Å	Al/Zn = 0.1
ZnAlO _y underlying barrier	18	7 Å	Al/Zn = 0.1
Ag	19	100 Å	
ZnAlO _y overlying barrier	20	17 Å	Al/Zn = 0.1
Top dielectric comprising:			
ZnAlO _x	22	185 Å	Al/Zn = 0.1
AlSi _x N _y	23	75 Å	Si/Al = 0.3

When the structure recited in the reference is substantially identical to that of the claims, the claimed properties or function are presumed inherent. *MPEP 2112.01*. Because the layer structure of Example 1 exemplifies the layer structure of presently pending claim 39 as demonstrated above, it would be expected that when the layer structure of Example 1 when heated according to the specifications of claim 39 that it would exhibit the same physical properties. Absent an objective showing to the contrary, the addition of the claimed physical properties to claim 39 fails to provide a patentable distinction over the prior art of record, meeting the limitations of claims 39-42.

Claim Rejections - 35 USC § 102/103

5. The following is a quotation of 35 U.S.C. 103(a) which forms the basis for all obviousness rejections set forth in this Office action:

(a) A patent may not be obtained though the invention is not identically disclosed or described as set forth in section 102 of this title, if the differences between the subject matter sought to be patented and the prior art are such that the subject matter as a whole would have been obvious at the time the invention was made to a person having ordinary skill in the art to which said subject matter pertains. Patentability shall not be negated by the manner in which the invention was made.

6. This application currently names joint inventors. In considering patentability of the claims under 35 U.S.C. 103(a), the examiner presumes that the subject matter of the various claims was commonly owned at the time any inventions covered therein were made absent any evidence to the contrary. Applicant is advised of the obligation under 37 CFR 1.56 to point out the inventor and invention dates of each claim that was not commonly owned at the time a later invention was made in order for the examiner to consider the applicability of 35 U.S.C. 103(c) and potential 35 U.S.C. 102(e), (f) or (g) prior art under 35 U.S.C. 103(a).

7. Claims 1-5, 10-14, 17, 22-27, 31-33, 35, 38-42 and 44 are under 35 U.S.C. 102(e) as anticipated by or, in the alternative, under 35 U.S.C. 103(a) as obvious over United States Patent no. 6,355,334, Rondeau et al.

Art Unit: 1775

Regarding claim 1

Applicant claims the following layer structure, (claim 1):

glass/silicon nitride/zinc oxide/Ag/dielectric (metal oxide)/Ag/dielectric

wherein the glass, silicon nitride, zinc oxide and first Ag layers are all located on and contacting each other without any other layers located between the aforementioned layers.

Rondeau et al disclose a transparent substrate provide with a thin film stack wherein the coated substrate can undergo heat treatments, (column 6, lines 44-47). The coating can have the following structure, (column 3, lines 55-60), meeting the requirements of claim 1:

Glass/SnO₂ or Si₃N₄:Al or AlN/ZnO or ZnO:Al/Ag/Ti or
NiCr/ZnO or SnO₂/SiO₂ or Al₂O₃ or SiO₂:Al₂O₃/SnO₂
or ZnO or SnZnO₂ or AlN or Si₃N₄:Al or (AlN/
Si₃N₄:Al) or (Si₃N₄:Al/AlN) or (SnO₂/SnZnO₂)

In the alternative, while not teaching a specific example with silicon nitride as the first dielectric layer it would have been within the skill of one in the art to select silicon nitride as it is listed as an equivalent to tin oxide and aluminum nitride.

Regarding claims 2-5, 10-14, and 22

When the structure recited in the reference is substantially identical to that of the claims, the claimed properties or function are presumed inherent. *MPEP 2112.01*. Because Rondeau et al (see above) exemplifies Applicant's claimed multilayer coating structure, the claimed physical properties relating to the visible light transmission, sheet resistance, and ΔE^* are inherently present in the prior art. Absent an objective showing to the contrary, the addition of the claimed physical properties to the claim language fails to provide patentable distinction over the prior art of record, meeting the requirements of claims 2-5 and 10-14.

Because the layer structure of Rondeau et al exemplifies the layer structure of presently pending claim 1 as demonstrated above, it would be expected that when the layer structure is heated according to the specifications of claim 22 that it would exhibit the same properties as claim 22. Absent an objective showing to the contrary, the addition of the

Art Unit: 1775

claimed physical properties to claim 22 fails to provide a patentable distinction over the prior art of record, meeting the limitations of claim 22.

Regarding claims 17 and 35

Materials such as aluminum can be used to dope the zinc oxide and silicon nitride layers, (column 3, lines 10-34), meeting the requirements of claims 17 and 35.

Regarding claim 23

Applicant claims the following layer structure, (claim 23):

glass/silicon nitride/zinc oxide/Ag/dielectric

wherein the silicon nitride is located directly on and contacting the glass substrate and the Ag layer is located directly on and contacting the zinc oxide layer. Rondeau et al disclose a transparent substrate provide with a thin film stack wherein the coated substrate can undergo heat treatments, (column 6, lines 44-47). The coating can have the following structure, (column 3, lines 55-60), meeting the requirements of claim 23:

Glass/SnO₂ or Si₃N₄:Al or AlN/ZnO or ZnO:Al/Ag/Ti or
NiCr/ZnO or SnO₂/SiO₂ or Al₂O₃ or SiO₂:Al₂O₃/SnO₂
or ZnO or SnZnO₂ or AlN or Si₃N₄:Al or (AlN/
Si₃N₄:Al) or (Si₃N₄:Al/AlN) or (SnO₂/SnZnO₂)

In the alternative, while not teaching a specific example with silicon nitride as the first dielectric layer it would have been within the skill of one in the art to select silicon nitride as it is listed as an equivalent to tin oxide and aluminum nitride.

Regarding claims 24-27, 31-33, and 38

When the structure recited in the reference is substantially identical to that of the claims, the claimed properties or function are presumed inherent. *MPEP 2112.01*. Because Rondeau et al (see above) exemplifies Applicant's claimed multilayer coating structure, the claimed physical properties relating to the visible light transmission, sheet resistance, and ΔE^* are inherently present in the prior art. Absent an objective showing to the contrary, the

addition of the claimed physical properties to the claim language fails to provide patentable distinction over the prior art of record, meeting the requirements of claims 24-27 and 32-33.

Because the layer structure of Rondeau et al exemplifies the layer structure of presently pending claim 23 as demonstrated above, it would be expected that when the layer structure is heated according to the specifications of claim 38 that it would exhibit the same properties as claim 38. Absent an objective showing to the contrary, the addition of the claimed physical properties to claim 38 fails to provide a patentable distinction over the prior art of record, meeting the limitations of claim 38.

Regarding claims 39-42

Applicant claims the following layer structure, (claim 39):

glass/silicon nitride/metal oxide/Ag/dielectric

wherein the silicon nitride is located directly on and contacting the glass substrate and the Ag layer is located directly on and contacting the metal oxide layer. Rondeau et al disclose a transparent substrate provide with a thin film stack wherein the coated substrate can undergo heat treatments, (column 6, lines 44-47). The coating can have the following structure, (column 3, lines 55-60):

Glass/SnO₂ or Si₃N₄:Al or AlN/ZnO or ZnO:Al/Ag/Ti or
NiCr/ZnO or SnO₂/SiO₂ or Al₂O₃ or SiO₂:Al₂O₃/SnO₂
or ZnO or SnZnO₂ or AlN or Si₃N₄:Al or (AlN/
Si₃N₄:Al) or (Si₃N₄:Al/AlN) or (SnO₂/SnZnO₂)

When the structure recited in the reference is substantially identical to that of the claims, the claimed properties or function are presumed inherent. *MPEP 2112.01*. Because the layer structure of Rondeau et al exemplifies the layer structure of presently pending claim 39 as demonstrated above, it would be expected that when the layer structure is heated according to the specifications of claim 39 that it would exhibit the same properties as claim 39. Absent an objective showing to the contrary, the addition of the claimed physical

properties to claim 39 fails to provide a patentable distinction over the prior art of record, meeting the limitations of claims 39-42.

In the alternative, while not teaching a specific example with silicon nitride as the first dielectric layer it would have been within the skill of one in the art to select silicon nitride as it is listed as an equivalent to tin oxide and aluminum nitride.

Regarding claim 44

The coated substrate, which is be held synonymous with a monolithic glass substrate, can be formed of a glass substrate with a multilayer coating formed thereon that is used as a window glazing, (column 4, lines 1-4), meeting the requirements of claim 44.

Claim Rejections - 35 USC § 103

8. Claims 1, 6-7, 15-16, 18, 23, 28-29, 34, 39, and 43 are rejected under 35 U.S.C. 103(a) as being unpatentable over United States Patent Application Publication no. 2003/0150711, Laird in view of United States Patent Application Publication no.2002/0102352, Hartig et al.

Regarding claims 1, 23, and 39

Applicant claims the following layer structure, (claim 1):

glass/silicon nitride/zinc oxide/Ag/dielectric (metal oxide)/Ag/dielectric

wherein the glass, silicon nitride, zinc oxide and first Ag layers are all located on and contacting each other without any other layers located between the aforementioned layers.

Applicant claims the following layer structure, (claim 23):

glass/silicon nitride/zinc oxide/Ag/dielectric

wherein the silicon nitride is located directly on and contacting the glass substrate and the Ag layer is located directly on and contacting the zinc oxide layer.

Applicant claims the following layer structure, (claim 39):

Art Unit: 1775

glass/silicon nitride/metal oxide/Ag/dielectric

wherein the silicon nitride is located directly on and contacting the glass substrate and the Ag layer is located directly on and contacting the metal oxide layer. The recitation of the coating have certain physical properties are considered as an optional feature as it is not recited as a positive limitation.

Laird discloses a coated article with high visible transmission and low emissivity wherein the layer structure of the coated article is as follows:

Layer	Preferred Range (Å)	More Preferred (Å)	Example (Å)
TiO ₂ (layer 3)	0-700 Å	100-400 Å	200 Å
ZnO _x (layer 7)	25-200 Å	40-150 Å	90 Å
Ag (layer 9)	50-250 Å	80-200 Å	130 Å
NiCrO _x (layer 11)	5-100 Å	15-50 Å	30 Å
SnO ₂ (layer 13)	0-1,000 Å	500-900 Å	680 Å
ZnO _x (layer 17)	25-200 Å	40-150 Å	90 Å
Ag (layer 19)	50-250 Å	80-220 Å	168 Å
NiCrO _x (layer 21)	5-100 Å	15-50 Å	30 Å
SnO ₂ (layer 23)	0-500 Å	70-200 Å	125 Å
Si ₃ N ₄ (layer 25)	0-500 Å	120-320 Å	220 Å

Layer 3, in the example set forth above is listed as TiO₂, is the first dielectric layer that can also be silicon nitride. Laird does not specifically disclose examples having silicon nitride in the place of titanium dioxide as the first dielectric layer.

Although no specific example has been listed using silicon nitride as the first dielectric layer, silicon nitride has been listed as an equivalent material for titanium dioxide, (page 2, section 0038). As such, it would have been within the skill of one in the art at the time of invention to substitute the silicon nitride for the titanium dioxide as the first dielectric layer.

Regarding claims 6-7, 15, 28-29, 34, and 43

Art Unit: 1775

According to Laird, the first dielectric layer comprised of silicon nitride contains the nitride in a stoichiometric or non-stoichiometric state having the formula Si_xN_y wherein x/y is in the range of 0.75-1.5. The Si-rich layer can have a refractive index ranging from 2.0-2.7, (page 2, section 0038).

Regarding claims 16

Laird discloses that the heat treatable, (page 1, section 0001), coated article can be a laminated windshield as demonstrated in Figure 2 and page 1, section 0036.

Regarding claim 18

Laird discloses the structural limitation of claim 1 above. Laird does not specifically disclose that a layer of silicon nitride should be placed between the ZnO and SnO_2 layers above the first Ag layer but below the second Ag layer.

Hartig et al disclose a haze resistant film stack wherein the intermediate layers formed between the first and second Ag layers has silicon nitride next to zinc oxide, (page 4, sections 0026-0028).


Laird and Hartig et al disclose inventions related to coated articles that can be used as vehicle and building window glazings. As such, it would be within the skill of one in the art at the time of invention to modify the layer structure of Laird by inserting a silicon nitride layer between the ZnO and SnO_2 located between the first and second Ag layers in order to prevent propagation of ZnO grain boundaries outside of the thickness of the layer in which ZnO is applied as well as significantly reduce the haze which may occur from high temperature treatment, (Hartig et al, page 4, section 0028).

Conclusion

Any inquiry concerning this communication or earlier communications from the examiner should be directed to Gwendolyn Blackwell whose telephone number is (571) 272-1533. The examiner can normally be reached on Monday - Thursday, 5:30 am - 4:00 pm.

If attempts to reach the examiner by telephone are unsuccessful, the examiner's supervisor, Deborah Jones can be reached on (571) 272-1535. The fax phone number for the organization where this application or proceeding is assigned is 703-872-9306.

Information regarding the status of an application may be obtained from the Patent Application Information Retrieval (PAIR) system. Status information for published applications may be obtained from either Private PAIR or Public PAIR. Status information for unpublished applications is available through Private PAIR only. For more information about the PAIR system, see <http://pair-direct.uspto.gov>. Should you have questions on access to the Private PAIR system, contact the Electronic Business Center (EBC) at 866-217-9197 (toll-free).


Gwendolyn Blackwell
Examiner
Art Unit 1775

gab